




Technical data sheet

STP FLEX

Sprayable Sealant

DESCRIPTION	
<p>STP FLEX is an advanced, STP-based hybrid sealant which gives highly flexible coats for sealing and protection of joint laps in automotive assemblies. The sealant is intended for application with special air spray guns and manual extrusion guns. The sprayable sealant can reproduce the OEM coating textures in motor vehicles. The curing action is based on the absorption of ambient moisture. The sprayable sealant is a product with the state-of-the-art in hybrid resin technologies, combining the strength of PUR with the flexibility, adhesion and weather resistance of siloxane compounds. The product is isocyanate free, which improves the work comfort and does not expose the user to harmful compounds. The product is easy to apply, while boasting high stability and adhesion to various substrates: carbon steels, galvanized steels, aluminium, glass, acrylic and epoxy primers, and concrete.</p>	
PROPERTIES	
Curing action	absorption of ambient moisture
Density	1.50 g/cm ³
Hardness, Shore A	50
Tensile strength (PN ISO 527)	1.2 MPa
Ultimate elongation (PN ISO 527)	80%
COATABILITY	
<p>Coatable with water-borne and solvent basecoats once the skin has cured and for 10 days after. STP FLEX is not suitable for coating with alkyd coats or any coats with anaerobic curing action.</p>	
SUBSTRATES	
Steel	Degrease, sand with P120, and degrease again.
Galvanized steel	Degrease, matt with an abrasive cloth, degrease.
Aluminium	Degrease, matt with an abrasive cloth, degrease.
Two-component acrylic primers	Sand with P360 and degrease.
Epoxy primers	Sand with P360 and degrease.
Concrete	Remove all dirt and contaminants first.
Glass	Degrease.
VOC CONTENT	
VOC II/B/e limit*	840 g/l
Actual VOC	65 g/l
* For ready to apply mixture acc. to EU Directive 2004/42/EC	



APPLICATION		
<p>Recommended application temperature: 15°C to 25°C. Operate the piston to feed out 1 to 2 cm of the product before installing the cartridge in the spray gun. The sealant is applied with special spray guns that must be operated according to their manufacturers' guidelines; or with manual or pneumatic extrusion guns. Certain finish textures require the sealant to be heated.</p>		
DRYING TIME		
	Skin formation time	15 minutes at 21°C, RH 50%
	Curing time	ca. 4 mm/24h at 21°C, RH 50%
COLOUR		
Ochre, black (see applicator color)		
EQUIPMENT CLEANING		
NC cleaners, ethyl acetate (until cured) Removal with power tools (once cured)		
STORAGE CONDITIONS		
Store in a dry room, away from sources of fire and heat.		
SHELF LIFE		
STP FLEX	12 months at 20°C in originally sealed cartridges.	
SAFETY		
See the Safety Data Sheet.		
OTHER INFORMATION		
Registration number: 000024104 The effectiveness of our systems results from laboratory research and many years of experience. The data contained herein meets the current knowledge about our products and their application potential. We ensure high quality, provided the user follows the instructions and the work is performed in accordance with good workmanship. It is necessary to perform a test application of the product due to its potentially different reaction with different materials. We may not be held liable for defects if the final result was affected by factors beyond our control.		